

## LOBADUR® WS Life

### One-Component Waterborne Finish for Parquet and Hardwood Floors

Article No:	11524	2004/42/CE
Level of Gloss:	Semi-glossy (ca. 33*)	EU limit value for this product
Package Size:	10l, 5l	(cat. A/i): 140g/l (2007/2010)
Giscode:	W3 - alternative product according to TRGS 617	This product contains max 50g/l VOC
Solids:	30 ± 1%	
Viscosity DIN 4:	25 ± 1s	

**Range of Use:** Parquet and hardwood floors with normal to heavy wear.

**Usage Information:**

- Shake material well
- Do not pre-lay material on the floor, use the LOBATool sealing bucket

**Set-up Recommendations for Parquet and Hardwood Floors:**

1. Prepare and prime surface
2. Drying of primer acc. to technical information
3. Apply LOBADUR® WS Life by using a roller
4. Drying, Intermediate Sanding, if needed, trowel one coat of LOBADUR® WS TopGel
5. Apply LOBADUR® WS Life by using a roller

**The Use of a Primer is Recommended:**

<b>With locking effect (for exotic wood)</b>	<b>To minimize side-bonding tendency</b>
<ul style="list-style-type: none"><li>• LOBADUR® WS Exotengrund</li></ul>	<ul style="list-style-type: none"><li>• LOBADUR® WS Exotengrund</li><li>• LOBADUR® WS EasyPrime</li></ul>

**Covering Tool:** LOBATool roller DeLuxe 120 or LOBATool roller Microfaser 100 - 120

**Covering Quantity:** Each roller application 100 - 120 ml/m<sup>2</sup> (8 - 10 m<sup>2</sup>/l), 10 – 12 ml / square foot

**Drying Time:** Earliest possible re-finishing after 4 to 6 hours, can be carefully walked on after 4 to 6 hours, light wear after 24 hours, complete wear after 5 days.

**Intermediate Sanding:** Able to re-finish without an intermediate sanding within the first 24 hours. After this time an intermediate sanding is necessary. An intermediate sanding before the last application will achieve a smooth surface.

**Thinner:** The finish is ready-to-use and cannot be diluted! In case of unfavourable conditions the drying can be delayed by adding a max. of 5% LOBADUR® WS Argo.

**Storage and Transportation:** +5°C to +25°C (41°F to 77°F), storable for 12 months, not a hazardous material according to ADR.

### The general information on the use of LOBADUR® WS products must be noticed!

**LOBA GmbH & Co. KG**  
Tel: +49 (0) 7156 357 220  
Fax: + 49 (0) 7156 357 211  
Mail: [service@loba.de](mailto:service@loba.de)

\* The gloss level is measured at 60°C. It depends on the thickness of the layer and the climatic conditions (temp, rel. air humidity) during drying. The data is not binding.